Exhibit 25

J3 resources, inc.

6110 W. 34th Street
Houston, TX 77092

(713) 290-0221
(713) 290-0248 fax
www.j3resources.com

July 13, 2018

Joseph D. Satterley, Esq.
Satterley & Kelley, PLLC.
8700 Westport Road, Suite 202
Louisville, KY 40242

RE: *Hayes v. Colgate, et al.* – Shower to Shower Samples

Dear Mr. Satterley:

J3 Resources, Inc. (J3) is an analytical laboratory accredited for the analysis of asbestos in air and bulk samples by Analytical Transmission Electron Microscopy (ATEM) and Polarized Light Microscopy (PLM) by the National Voluntary Laboratory Accreditation Program (NVLAP) {Lab Code 200525}.

On May 23, 2018, J3 received sixteen (16) Shower to Shower talcum powder samples from Joseph D. Satterley, Esq. as labeled below:

Sample 20180070-07D	Sample 20180061-65D
Sample 20180061-37D	Sample 20180061-66D
Sample 20180061-38D	Sample 20180061-02D
Sample 20180061-45D	Sample 20180061-10D
Sample 20180061-50D	Sample 20180061-15D
Sample 20180061-51D	Sample 20180061-21D
Sample 20180061-52D	Sample 20180061-31F
Sample 20180061-63D	Sample 20180061-31G

Each sample was contained in a sealed jar and contained between 12.8g - 16.7g of material. The package contained a letter from Mr. Satterley authorizing analysis of all 16 talc samples for the presence of regulated asbestos. J3 analyzed the talcum powder samples for the presence and percentage of regulated asbestos utilizing the following appropriate methods:

ISO 22262-1 (2012) ***Air quality — Bulk materials — Part 1: Sampling and qualitative determination of asbestos in commercial bulk materials***

ISO 22262-2 (2014) ***Air quality — Bulk materials — Part 2: Quantitative determination of asbestos by gravimetric and microscopical methods***

ISO 22262-3 (2016) ***Air quality — Bulk materials — Part 3: Quantitative determination of asbestos by X-ray diffraction method***

EXHIBIT
16
Page
PENGAD 800-631-6989

The summary of results of this study by ISO 22262 (Parts 1-3) are as follows:

Talc was found in each of the samples in various forms – plates, fibers, and ribbons. No regulated asbestos was detected in any of the Polarized Light Microscopy analyses conducted on any of the 16 samples indicating that any asbestos present was below the detection limit for this method.

Following gravimetric reduction and heavy liquid separation of all 16 submitted samples, Analytical Transmission Electron Microscopy analysis found regulated asbestos in 11 of the 16 submitted samples. The regulated asbestos fibers were all Anthophyllite asbestos.

X-Ray-Diffraction analysis did not indicate a significant peak in the appropriate range for amphibole asbestos in any of the 16 samples and would also indicate any asbestos present is below the detection limit for this method.

These reports are considered highly confidential and the sole property of the customer. J3 Resources, Inc. will not discuss any part of this study with personnel other than those authorized by the customer. This report shall not be reproduced, except in full, without written approval from J3 Resources, Inc. Samples will be returned or disposed of after 90 (ninety) days unless longer storage is requested. If you should have any questions about this report, please feel free to call me at 713-290-0221.

Sincerely,

Lee W. Poye
Vice President
J3 Resources, Inc.

JH1898969
Analysis of Shower to Shower Talc Samples



For:
Joseph D. Satterley, Esquire
Satterley & Kelley, PLLC.
8700 Westport Road, Suite 202
Louisville, KY 40242
(502) 589-5600

By:
Lee W. Poye
Vice President
J3 Resources, Inc.
6110 W 34th Street
Houston, TX 77092

July 13, 2018

INTRODUCTION

The data presented in this report is based on analytical analysis of sixteen (16) Shower to Shower talcum powder samples as received by J3 Resources, Inc. from Joseph D. Satterley, Esq. of Satterley & Kelley, PLLC, on May 23, 2018. The samples were forwarded to and received by J3 via Federal Express Delivery (Air Bill Number 811928628966).

The package contained sixteen (16) Shower to Shower talcum powders each individually sealed within a labeled plastic jar and a letter detailing the scope of work requested. Each jar was sealed with black electrical tape. The samples were logged into the J3 Laboratory Information Management System (LIMS) and the project was assigned the J3 job number JH1898969. Each sample was assigned a specific J3 identification number.

J3 Resources Inc. purchased a four-ounce bottle of *Johnson's Baby Powder* (Lot # 0354RA) from Walgreen's Pharmacy on June 11, 2014 to use as a Laboratory Control Sample.

The "16 Shower to Shower Talc" talcum powder samples were assigned the specific J3 identification numbers as follows:

Client ID		J3 Sample ID
Sample 20180070-07D	=	STS 1601A
Sample 20180061-37D	=	STS 1602A
Sample 20180061-38D	=	STS 1603A
Sample 20180061-45D	=	STS 1604A
Sample 20180061-50D	=	STS 1605A
Sample 20180061-51D	=	STS 1606A
Sample 20180061-52D	=	STS 1607A
Sample 20180061-63D	=	STS 1608A
Sample 20180061-65D	=	STS 1609A
Sample 20180061-66D	=	STS 1610A
Sample 20180061-02D	=	STS 1611A
Sample 20180061-10D	=	STS 1612A
Sample 20180061-15D	=	STS 1613A
Sample 20180061-21D	=	STS 1614A
Sample 20180061-31F	=	STS 1615A
Sample 20180061-31G	=	STS 1616A

PROCEDURES

As directed, J3 analyzed each of the talcum powder samples submitted following procedures in ISO 22262-1 (2012), ISO 22262-2 (2014), and ISO 22262-3 (2016):

ISO 22262-1 (2012); Air quality — Bulk materials — Part 1: Sampling and qualitative determination of asbestos in commercial bulk materials.

This method utilizes Polarized Light Microscopy (PLM) to identify asbestos structures based on unique optical properties present in bulk materials. This method was designed to be utilized when asbestos fibers can be readily separated from the matrix material for identification. Following this analysis, samples may be further characterized by Analytical Transmission Electron Microscopy to improve detection limits. PLM specifically is limited by resolution of the optical microscope and matrix of the sample, thus, fibers smaller than 0.2µm are unlikely to be detected. With appropriate matrix reduction procedures and depending on the analytical technique utilized, the limit of detection with this method can be significantly lower than 0.01%.

ISO 22262-2 (2014) Air quality — Bulk materials — Part 2: Quantitative determination of asbestos by gravimetric and microscopical methods

This method was designed to quantify samples whose asbestos mass fractions are below 5% by weight and specifically applies to commercially available products containing talc. Samples that contain asbestos at low mass fractions within the sample matrix require additional preparation steps or else microscopic analysis proves to be unreliable. The ability to detect asbestos in this lower range depends on the proportion of non-asbestos material which can be removed from the sample using gravimetric methods. With appropriate matrix reduction procedures (gravimetric reduction, heavy liquid separation, etc.) and the use of Analytical Transmission Electron Microscope, the limit of detection can be significantly lower than 0.001%.

ISO 22262-3 (2016) Air quality — Bulk materials — Part 3: Quantitative determination of asbestos by X-ray diffraction method

This method utilizes XRD to determine the weight percent of mineral phases in a pelletized sample. This method may allow for a detection limit of 0.1% to be reached if sufficient material is analyzed for a sufficient time. This method cannot differentiate between asbestiform and non-asbestiform phases of minerals.

DEFINITIONS

Regulated Asbestos

The term 'Regulated Asbestos' as used in this document refers to the six asbestiform minerals identified by OSHA, NIOSH, and/or USEPA and specifically defined as follows in the methods utilized by this study.

From USEPA 600/R-93/116: – A commercial term applied to the asbestiform varieties of six different minerals. The asbestos types are chrysotile (asbestiform serpentine), amosite (asbestiform grunerite), crocidolite (asbestiform riebeckite), and asbestiform anthophyllite, asbestiform tremolite, and asbestiform actinolite. The properties of asbestos that caused it to be widely used commercially are: 1) its ability to be separated into long, thin, flexible fibers; 2) high tensile strength; 3) low thermal and electrical conductivity; 4) high mechanical and chemical durability, and 5) high heat resistance.

From OSHA ID-191: Asbestos: A term for naturally occurring fibrous minerals. Asbestos includes chrysotile, cummingtonite-grunerite asbestos (amosite), anthophyllite asbestos, tremolite asbestos, crocidolite, actinolite asbestos and any of these minerals which have been chemically treated or altered. The precise chemical formulation of each species varies with the location from which it was mined. Nominal compositions are listed:

Chrysotile
$Mg_3Si_2O_5(OH)_4$

Crocidolite (Riebeckite asbestos)
$Na_2Fe_3^{2+}Fe_2^{3+}Si_8O_{22}(OH)_2$

Cummingtonite-Grunerite asbestos (Amosite)
$(Mg,Fe)_7Si_8O_{22}(OH)_2$

Tremolite-Actinolite asbestos
$Ca_2(Mg,Fe)_5Si_8O_{22}(OH)_2$

Anthophyllite asbestos
$(Mg,Fe)_7Si_8O_{22}(OH)2$

NOTE: Anthophyllite and cummingtonite are both regulated asbestos types. For the scope of this report, the term anthophyllite includes all minerals in the anthophyllite - ferro-anthophyllite - cummingtonite solid solution series as documented in Deer *et. al.*, 1974.

Cleavage Fragment

As defined by ISO 22262-2, a cleavage fragment is a fragment of a crystal that is bounded by cleavage faces. Crushing of non-asbestiform amphibole generally yields elongated fragments that conform to the definition of a fiber, but rarely have aspect ratios exceeding 30:1.

In this report, to differentiate cleavage fragments from fibers, J3 Resources, Inc. will follow the guidelines detailed in the OSHA standard (OSHA 29 CFR 1915.1001 App K) as detailed below.

"Most cleavage fragments of the asbestos minerals are easily distinguishable from true asbestos fibers. This is because true cleavage fragments usually have larger diameters than 1 µm. Internal structure of particles larger than this usually shows them to have no internal fibrillar structure. In addition, cleavage fragments of the monoclinic amphiboles show inclined extinction under crossed polars with no compensator. Asbestos fibers usually show extinction at zero degrees or ambiguous extinction if any at all. Morphologically, the larger cleavage fragments are obvious by their blunt or stepped ends showing prismatic habit. Also, they tend to be acicular rather than filiform.

Where the particles are less than 1 µm in diameter and have an aspect ratio greater than or equal to 3:1, it is recommended that the sample be analyzed by SEM or TEM if there is any question whether the fibers are cleavage fragments or asbestiform particles."

Limit of quantification

From ISO 22262-2 (2014) - The limit of quantification is defined as the detection and identification of one fiber or fiber bundle in the amount of sample examined. The limit of quantification that can be achieved depends on:

a) the nature of the matrix of the sample;
b) the size of the asbestos fibers and bundles;
c) the use of appropriate sample preparation and matrix reduction (gravimetric) procedures;
d) the amount of time expended on examination of the sample; and,
e) the method of analysis used, PLM, SEM or TEM.

With appropriate matrix reduction procedures that are selected based on the nature of the sample, the limit of quantification can be lower than 0.001 %.

MATERIALS AND EQUIPMENT

Optical macroscopic sample analysis was performed by using a Leica S6D Stereoscope equipped with a Leica L2 light source and digital camera. PLM analysis was conducted with a Leica DM 750P equipped with a 10X/0.25 polarized dispersion staining objective, a 40X/0.65 objective, a 10x/0.25 objective, a 4x/0.10 objective, and 10X oculars, also fitted with a digital camera. Analysis was conducted between 40x – 400x magnification.

Analytical Transmission Electron Microscope (ATEM) analysis was performed using a JEOL 1200EX ATEM at 100kV equipped with an IXRF Energy Dispersive X-ray Spectroscopy (EDS) analysis system and a Super Ultra-Thin Window (SUTW) high-angle AAT detector. Analysis was conducted between 3,000x and 25,000x magnification. Any particle of interest was analyzed as to its morphological character, elemental composition using EDS, and crystalline pattern using Selected Area Electron Diffraction (SAED). Images of interest were recorded with a digital camera.

X-ray powder diffraction was conducted using a PANalytical CubiX^3 HR X-Ray Diffractometer (XRD) with Bragg-Brentano^{HD} optics.

RESULTS

Sample	PLM Analysis *ISO 22262-1*	TEM Analysis *ISO 22262-2*		XRD Analysis *ISO 22262-3*
	Asbestos Type	Asbestos Type	Mass Fraction	Asbestos Type
20180070-07D	None Detected	Anthophyllite	0.00073%	None Detected
20180061-37D	None Detected	Anthophyllite	0.000030%	None Detected
20180061-38D	None Detected	Anthophyllite	0.0037%	None Detected
20180061-45D	None Detected	Anthophyllite	0.0019%	None Detected
20180061-50D	None Detected	None Detected	< 0.000000025%	None Detected
20180061-51D	None Detected	None Detected	< 0.000000024%	None Detected
20180061-52D	None Detected	Anthophyllite	0.0040%	None Detected
20180061-63D	None Detected	Anthophyllite	0.000035%	None Detected
20180061-65D	None Detected	Anthophyllite	0.0092%	None Detected
20180061-66D	None Detected	None Detected	< 0.000000025%	None Detected
20180061-02D	None Detected	None Detected	< 0.000000025%	None Detected
20180061-10D	None Detected	Anthophyllite	0.000026%	None Detected
20180061-15D	None Detected	Anthophyllite	0.0013%	None Detected
20180061-21D	None Detected	None Detected	< 0.000000022%	None Detected
20180061-31F	None Detected	Anthophyllite	0.0029%	None Detected
20180061-31G	None Detected	Anthophyllite	0.00052%	None Detected

QUALITY ASSURANCE - QUALITY CONTROL

In addition to normal QA/QC required by the various accrediting bodies, J3 opted to employ additional QA/QC measures specifically for this project. To rule out the possibility of contamination of samples while in the laboratory, J3 Resources, Inc. prepared and analyzed Control Blanks with all talc samples submitted. Additionally, air monitoring was conducted and analyzed using ASTM D6281 protocols during all sample preparations. For a Control Blank, J3 used a currently available brand name consumer talcum powder which was prepared and analyzed alongside preparation and analysis of all customer samples generated during this project.

No regulated asbestos was detected in the Control Blank.

No regulated asbestos was detected in any of the air monitoring samples.

REFERENCES

Asbestos Hazard Emergency Response Act. Appendix A to Subpart E - Interim Transmission Electron Microscopy Analytical Methods. U.S. EPA 40 CFR 763. Asbestos-containing materials in schools, final rule and notice. *Federal Register* 1987; 52(210):41857-94.

ASTM. Standard Practice for Asbestos Detection Limit Based on Count. ASTM Designation D6620-06 (Reapproved 2010). West Conshohocken, PA: American Society for Testing and Materials; 2006.

ASTM. Standard Test Method for Airborne Asbestos Concentration in Ambient and Indoor Atmospheres as Determined by TEM Direct Transfer. ASTM Designation D6281-06. West Conshohocken, PA: American Society for Testing and Materials; 2006.

Deer, W.A., Howie, R.A., Zussman, J., *Rock Forming Minerals*, Longman, Thetford, UK, 1974.

Chatfield EJ. A validated method for gravimetric determination of low concentrations of asbestos in bulk materials. In: Beard ME, Rook HL, editors. *Advances in Environmental Measurement Methods for Asbestos.* ASTM STP 1342. West Conshohocken, PA: ASTM 2000. pp. 90-110.

International Standards Organization, ISO 13794. Ambient air: determination of asbestos fibers Indirect-transfer transmission electron microscopy method. Geneva, Switzerland: International Standards Organization; 1999.

International Standards Organization, ISO 22262. Air Quality – Bulk Materials – Part 1: Sampling and qualitative determination of asbestos in commercial bulk materials, 2012.

International Standards Organization, ISO 22262. Air Quality – Bulk Materials – Part 2: Quantitative Determination of Asbestos by Gravimetric and Microscopical Methods, 2014.

International Standards Organization, ISO 22262. Air Quality – Bulk Materials – Part 3: Quantitative Determination of asbestos by X-ray diffraction method, 2016.

Millette, JR, 2011. Asbestos Analysis Methods. In: Dodson, RF and Hammar, SP editors: Asbestos-Risk Assessment, Epidemiology, and Health Effects – 2nd ed., Taylor and Francis Publishing. pp. 23-48.

National Institute of Occupational Safety and Health, NIOSH 7400. Asbestos and Other Fibers by Phase Contrast Microscopy (PCM) – Method 7400. *NIOSH Manual of Analytical Methods*. 4th ed. Washington, DC: U.S. Dept. of Health & Human Services;1994. NIOSH Publication #94-113.

National Institute of Standards and Technology, Certificate of Analysis – Standard Reference Material 1867a - Uncommon Commercial Asbestos. Gaithersburg, MD. March 2003.

Occupational Safety and Health Administration: Rules and Regulations, Department of Labor: 29 CFR Parts 1910, 1915 and 1926, 59 FR 40964, RIN: 1218-AB25; Occupational Exposure to Asbestos; August 1994-Final Rule; Appendix B of 1910.1001; 1. Introduction and Appendix K of 1915.1001; Polarized Light Microscopy of Asbestos. 3.5 Analytical Procedure.

U.S. Environmental Protection Agency. Method for the Determination of Asbestos in Bulk Building Materials. EPA-600/R93/116. Washington DC U.S. Environmental Protection Agency. July 1993.

Verkouteren, J.R.; Wylie, A.G.; *The Tremolite-Actinolite-Ferro-Actinolite Series: Systematic Relationships Among Cell Parameters, Composition, Optical Properties and Habit, and Evidence of Discontinuities*; American Mineralogist, Vol. 85, pp. 1239-1354 (2000).

Appendix A

General Observations of Fibrous Components

Typical ATEM Grid Loading

StS-10_003
Filter Loading
Microscopist: LWP

10 µm
HV=100kV
Direct Mag: 200 x
J3 Resources, Inc.

Talc Fiber (Typical)

Morphology and Diffraction Pattern

Talc Ribbon (Typical) - Morphology
Demonstrating Typical Kink

StS-09-001.tif
Talc Ribbon
Microscopist: LWP

500 nm
HV=100kV
Direct Mag: 30000 x
J3 Resources, Inc.

Talc Ribbon (Typical) - Morphology
(0° and 40° Rotation)

Anthophyllite Fiber

Morphology and Diffraction Pattern



Anthophyllite Fiber

Morphology – Aspect Ratios > 20:1





APPENDIX B

LABORATORY REPORTS

Sample 20180070-07D

(J3 Lab ID: STS 1601A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180070-07D

The sample was a white powder containing 85% medium to large platy Talc particles (100µm to >200µm in size) and Talc rods. The remaining 15% percent was composed of carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180070-07D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 30-Jun-2018

Weight of Sample*:	0.0176 g	**Filter Size:**	25 mm
Percent of Original Sample*:	81%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	3.5	0.25	14	Anthophyllite
2	6	0.4	15	Anthophyllite
3	7.5	0.2	37.5	Anthophyllite
4	11	0.6	18.3	Anthophyllite
5	4	0.25	16	Anthophyllite
6	14	1.1	12.7	Anthophyllite
7	8.5	0.4	21.3	Anthophyllite
8	9	0.6	15	Anthophyllite
9	10	0.9	11.1	Anthophyllite
AVERAGE	8.2	0.52	15.6	

Total Asbestos Structures:	9
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5

Asbestos Mass Fraction: **0.00090%**

Asbestos Mass Fraction of Original Sample: **0.00073%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180070-07D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 1 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1									
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		1	3.5 x 0.25	Anthophyllite	Yes	01	02	Zone Axis [1 0 1]
	B9		NSD						
	B10		NSD						
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
2									
	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						
	C1		NSD						
	C2		2	6 x 0.40	Anthophyllite	Yes	07	08	
	C3		NSD						
	C4		NSD						
	C5		3	7.5 x 0.20	Anthophyllite	Yes	09		

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180070-07D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	C5		4	11 x 0.60	Anthophyllite	Yes			
	C6		NSD						
	C7		5	4 x 0.25	Anthophyllite	Yes	10	11	
	C8		NSD						
	C9		6	14 x 1.10	Anthophyllite	Yes	06	05	
	C10		7	8.5 x 0.40	Anthophyllite	Yes	03	04	
3									
	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		8	9 x 0.60	Anthophyllite	Yes	13	12	
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
4									
	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		9	10 x 0.90	Anthophyllite	Yes			
	H5		NSD						
	H6		NSD						
	H7		NSD						
	H8		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180070-07D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4									
	H9		NSD						
	H10		NSD						
	E1		NSD						
	E2	✓	NA		Talc	Yes	14	15	Fiber
	E3		NSD						
	E4		NSD						
	E5		NSD						
	E6		NSD						
	E7		NSD						
	E8		NSD						
	E9		NSD						
	E10		NSD						

Sample 20180070-07D
Structure 1 - Morphology

StS-01 Full Quant_001
Anthophyllite
GO - 88
11:11:46 6/27/2018
Microscopist: LWP

600 nm
HV=100kV
Direct Mag: 25000 x
J3 Resources, Inc.

Sample 20180070-07D
Structure 1 – Diffraction Pattern and EDS





Sample 20180070-07D
Structure 2 - Morphology



StS-01 Full Quant_007
Anthophyllite
GO - C2
Microscopist: LWP

600 nm
HV=100kV
Direct Mag: 20000 x
J3 Resources, Inc.

Sample 20180070-07D
Structure 2 – Diffraction Pattern and EDS



Sample 20180070-07D
Structure 3 – Morphology and EDS

StS-01 Full Quant_009
Anthophyllite
GO - C5
Microscopist: LWP

1 µm
HV=100kV
Direct Mag: 15000 x
J3 Resources, Inc.



Sample 20180070-07D
Structure 5 - Morphology



StS-01 Full Quant_010
Anthophyllite
GO - C7
Microscopist: LWP

600 nm
HV=100kV
Direct Mag: 25000 x
J3 Resources, Inc.

Sample 20180070-07D
Structure 5 – Diffraction Pattern



Sample 20180070-07D
Structure 6 - Morphology

StS-01 Full Quant_006
Anthophyllite
GO - C9
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 7500 x
J3 Resources, Inc.

Sample 20180070-07D
Structure 6 – Diffraction Pattern and EDS





Sample 20180070-07D
Structure 7 - Morphology



StS-01 Full Quant_003 ZA.tif
Anthophyllite - SAED - ZA [1 0 1]
GO - C10
Microscopist: LWP
Microscopist: LWP

600 nm
HV=100kV
Direct Mag: 25000 x
J3 Resources, Inc.

Sample 20180070-07D
Structure 7 – Diffraction Pattern and EDS





Sample 20180070-07D
Structure 8 - Morphology



StS-01 Full Quant_013
Anthophyllite
Grid 3 GO - I4
Microscopist: LWP

1 µm
HV=100kV
Direct Mag: 12000 x
J3 Resources, Inc.

Sample 20180070-07D
Structure 8 – Diffraction Pattern



SCS-01 Full Quant_012
Anthophyllite - SAED
Grid 3 GO - I4
Microscopist: LWP

0.2 (1/Å)
HV=100kV
Cam Len: 0.8000 m
J3 Resources, Inc.

Sample 20180070-07D
Talc Fiber (GO E2) - Morphology



Sample 20180070-07D
Talc Fiber (GO E2) - Diffraction Pattern



Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180070-07D



No Amphibole Peak Present

Sample 20180061-37D

(J3 Lab ID: STS 1602A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-37D

The sample was a white powder containing 85% medium to large platy Talc particles (100µm to >200µm in size) and Talc rods. The remaining 15% percent was composed of carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-37D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 30-Jun-2018

Weight of Sample*:	0.0174 g	**Filter Size:**	25 mm
Percent of Original Sample*:	80%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	16	0.3	53.3	Anthophyllite
AVERAGE	**16**	**0.3**	**53.3**	

Total Asbestos Structures:	1
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5
Asbestos Mass Fraction:	**0.000037%**
Asbestos Mass Fraction of Original Sample:	**0.000030%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-37D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 1 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1									
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
	H1	✓	NA	9.6 x 2.60	Tremolite	Yes	06	07	Cleavage Fragment
	H2		NSD						
	H3		NSD						
	H4	✓	NA	19 x 0.50	Talc	Yes	09		Ribbon
	H5	✓	NA	36 x 1.20	Talc	Yes	10	11	Fiber
	H6		NSD						
	H7	✓	NA	13 x 1.30	Talc	Yes			Fiber
	H8		NSD						
	H9		NSD						
	H10		NSD						
2									
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		1	16 x 0.30	Anthophyllite	Yes	12	13	
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10	✓	NSD	31 x 2.70	Talc	Yes			
	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-37D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2									
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10	✓	NA	31 x 2.70	Talc	Yes			
3									
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						
	J1		NSD						
	J2		NSD						
	J3		NSD						
	J4		NSD						
	J5		NSD						
	J6		NSD						
	J7		NSD						
	J8		NSD						
	J9		NSD						
	J10		NSD						
4									
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-37D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4									
	B9		NSD						
	B10	✓	NA	16 x 0.60	Talc	Yes			Ribbon
	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						

Sample 20180061-37D

Tremolite Cleavage Fragment (GO H1) - Morphology



StS-02_006
Tremolite < 5:1 AR
GO - H1
Microscopist: LWP

1 µm
HV=100kV
Direct Mag: 10000 x
J3 Resources, Inc.

Sample 20180061-37D
Tremolite Cleavage Fragment (GO H1)
Diffraction Pattern and EDS



Sample 20180061-37D
Talc (GO H4) - Morphology

StS-02_009
Talc Ribbon
GO - H4
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 7500 x
J3 Resources, Inc.

Sample 20180061-37D
Talc (GO H5) - Morphology



Sample 20180061-37D
Talc (GO H5) – Diffraction Pattern



Sample 20180061-37D
Structure 1 - Morphology



StS-02_012
Anthophyllite
Grid B GO - C6
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 6000 x
J3 Resources, Inc.

Sample 20180061-37D
Structure 1 – Diffraction Pattern and EDS



StS-02_013 ZA.tif
Anthophyllite - SAED ZA [1 0 0]
Grid B GO - C6
Microscopist: LWP

0.2 (1/A)
HV=100kV
Cam Len: 0.8000 m
J3 Resources, Inc.



Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-37D



No Amphibole Peak Present

Sample 20180061-38D

(J3 Lab ID: STS 1603A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-38D

The sample was a white powder containing 60% medium to large platy Talc particles (100µm to >200µm in size). The remaining 40% percent was composed of 20% starch and 20% carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-38D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 30-Jun-2018

Weight of Sample*:	0.0172 g	**Filter Size:**	25 mm
Percent of Original Sample*:	65%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	3.5	0.5	7	Anthophyllite
2	19	1.6	11.8	Anthophyllite
3	7	1.1	6.4	Anthophyllite
4	3.5	0.4	8.8	Anthophyllite
5	6	0.3	20	Anthophyllite
6	20	2.8	7.1	Anthophyllite
7	3	0.25	12	Anthophyllite
AVERAGE	**8.9**	**0.99**	**8.9**	

Total Asbestos Structures:	7
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5

Asbestos Mass Fraction of Original Sample: **0.0056%**

Asbestos Mass Fraction of Original Sample: **0.0037%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-38D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1									
	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						
	A9	✓	NA	2.8 x 0.60	Anthophyllite	Yes	01	02	Cleavage Fragment
	A10		NSD						
	F1		NSD						
	F2		NSD						
	F3		1	3.5 x 0.50	Anthophyllite	Yes			
	F4		NA						
	F5		NA						
	F6		NSD						
	F7		NA						
	F8		2	19 x 1.60	Anthophyllite	Yes			
	F9		NSD						
	F10		NSD						
2									
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						
	H1	✓	NA	7.5 x 1.10	Anthophyllite	Yes			Cleavage Fragment
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-38D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2									
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						
3									
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4	✓	NA	6 x 0.90	Anthophyllite	Yes	03	04	Transitional
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		3	7 x 1.10	Anthophyllite	Yes			
	G10		4	3.5 x 0.40	Anthophyllite	Yes	05	06	
4									
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		5	6 x 0.30	Anthophyllite	Yes			
	D7		NSD						
	D8		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-38D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4									
	D9		NSD						
	D10		NSD						
	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		6	20 x 2.80	Anthophyllite	Yes	07		
	H6		NSD						
	H7		7	3 x 0.25	Anthophyllite	Yes	08		
	H8		NSD						
	H9		NSD						
	H10		NSD						

Sample 20180061-38D
Anthophyllite (GO A9 - Cleavage Fragment) Morphology



StS-03 Full Quant_001
Anthophyllite Cleavage Fragment
GO-A9
Microscopist: LWP

600 nm
HV=100kV
Direct Mag: 20000 x
J3 Resources, Inc.

Sample 20180061-38D
Anthophyllite (GO A9 - Cleavage Fragment)
Diffraction Pattern and EDS





Sample 20180061-38D
Anthophyllite (GO D4 – Transitional)
Morphology



Sample 20180061-38D
Anthophyllite (GO D4 - Transitional)
Diffraction Pattern

Sample 20180061-38D
Structure 4 - Morphology



Sample 20180061-38D
Structure 4 – Diffraction Pattern and EDS



Sample 20180061-38D
Structure 6 - Morphology



Sample 20180061-38D
Structure 7 - Morphology



StS-03 Full Quant_008
Anthophyllite
GO-H7
Microscopist: LWP

500 nm
HV=100kV
Direct Mag: 25000 x
J3 Resources, Inc.

Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-38D



No Amphibole Peak Present

Sample 20180061-45D

(J3 Lab ID: STS 1604A)



Sample as received by J3 Resources, Inc.

resources, inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-45D

The sample was a white powder containing 85% medium to large platy Talc particles (100µm to >200µm in size) and Talc rods. The remaining 15% percent was composed of carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate

100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-45D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 30-Jun-2018

Weight of Sample*:	0.0175 g	**Filter Size:**	25 mm
Percent of Original Sample*:	79%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	19	2.20	8.6	Anthophyllite
AVERAGE	19	2.20	8.6	

Total Asbestos Structures:	1
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5
Asbestos Mass Fraction:	**0.0024%**
Asbestos Mass Fraction of Original Sample:	**0.0019%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-45D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1									
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5	✓	NA	14 x 0.60	Talc	Yes	01	02	Fiber
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						
	I1		NSD						
	I2		NSD						
	I3	✓	NA	21 x 0.80	Talc	Yes	05		Ribbon
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		1	19 x 2.20	Anthophyllite	Yes	03	04	
	I8		NSD						
	I9		NSD						
	I10		NSD						
2									
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-45D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 2 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2									
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						
3									
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10	✓	NA	17 x 2.50	Talc	Yes			Fiber
	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4	✓	NA	26 x 0.30	Talc	Yes			Ribbon
	G5	✓	NA	9 x 0.50	Talc	Yes			Ribbon
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10	✓	NA	8 x 1.00	Talc	Yes			Fiber
4									
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-45D

Analyst: Lee Poye
Date: 30-Jun-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4									
	D9		NSD						
	D10		NSD						
	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						

Sample 20180061-45D
Talc (GO C5) - Morphology



StS-04 Full Quant_001
Talc Fiber
GO-C5
Microscopist: LWP

1 µm
HV=100kV
Direct Mag: 10000 x
J3 Resources, Inc.

Sample 20180061-45D
Talc (GO C5) – Diffraction Pattern

Sample 20180061-45D
Talc (GO I3) - Morphology

StS-04 Full Quant_005
Talc Ribbon
GO-I3
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 6000 x
J3 Resources, Inc.

Sample 20180061-45D
Structure 1 - Morphology

SES-04 Full Quant_003
Anthophyllite
GO-I7
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 6000 x
J3 Resources, Inc.

Sample 20180061-45D
Structure 1 – Diffraction Pattern and EDS



Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-45D



No Amphibole Peak Present

Sample 20180061-50D

(J3 Lab ID: STS 1605A)



Sample as received by J3 Resources, Inc.

J3 resources, inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-50D

The sample was a white powder containing 85% medium to large platy Talc particles (100µm to >200µm in size) and Talc rods. The remaining 15% percent was composed of carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate

100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-50D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 4-Jul-2018

Weight of Sample*:	0.0179 g	**Filter Size:**	25 mm
Percent of Original Sample*:	79%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
N/D	N/A	N/A	N/A	None Detected
AVERAGE	N/A	N/A	N/A	

Total Asbestos Structures: 0

Asbestos Mass Fraction: < 0.000000031%

Asbestos Mass Fraction of Original Sample: < 0.000000025%

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-50D

Analyst: Lee Poye
Date: 4-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1									
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4	✓	NA	34 x 2.30	Talc	Yes			Fiber
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						
2									
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5	✓	NA	7 x 0.70	Talc	Yes			Fiber
	B6		NSD						
	B7		NSD						
	B8	✓	NA	7.5 x 0.25	Talc	Yes	01	02	Fiber
	B9		NSD						
	B10		NSD						
	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-50D

Analyst: Lee Poye
Date: 4-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2									
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10		NSD						
3									
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						
4									
	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-50D

Analyst: Lee Poye
Date: 4-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4									
	A9		NSD						
	A10		NSD						
	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5	✓	NA	88 x 2.50	Talc	Yes			Ribbon
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						

Sample 20180061-50D
Talc (GO B8) - Morphology



Sample 20180061-50D
Talc (GO B8) – Diffraction Pattern



StS-05 Full Quant_002
Talc - SAED
GO - B8
Microscopist: LWP

0.2 (1/A)
HV=100kV
Cam Len: 0.8000 m
J3 Resources, Inc.

Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-50D



No Amphibole Peak Present

Sample 20180061-51D

(J3 Lab ID: STS 1606A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-51D

The sample was a white powder containing 85% medium to large platy Talc particles (100µm to >200µm in size) and Talc rods. The remaining 15% percent was composed of carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-51D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 4-Jul-2018

Weight of Sample*:	0.0176 g	**Filter Size:**	25 mm
Percent of Original Sample*:	77%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
N/D	N/A	N/A	N/A	None Detected
AVERAGE	N/A	N/A	N/A	

Total Asbestos Structures: 0

Asbestos Mass Fraction: < 0.000000032%

Asbestos Mass Fraction of Original Sample: < 0.000000024%

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-51D

Analyst: Lee Poye
Date: 4-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1									
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
	E1		NSD						
	E2		NSD						
	E3		NSD						
	E4		NSD						
	E5		NSD						
	E6		NSD						
	E7		NSD						
	E8		NSD						
	E9		NSD						
	E10		NSD						
2									
	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10		NSD						
	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-51D

Analyst: Lee Poye
Date: 4-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2									
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						
3									
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
4									
	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-51D

Analyst: Lee Poye
Date: 4-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4									
	I9		NSD						
	I10		NSD						
	J1		NSD						
	J2		NSD						
	J3		NSD						
	J4		NSD						
	J5		NSD						
	J6		NSD						
	J7		NSD						
	J8		NSD						
	J9		NSD						
	J10		NSD						

resources, inc.

Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-51D



No Amphibole Peak Present

Sample 20180061-52D

(J3 Lab ID: STS 1607A)

Sample as received by J3 Resources, Inc.

J3 resources, inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-52D

The sample was a white powder containing 60% medium to large platy Talc particles (100µm to >200µm in size). The remaining 40% percent was composed of 20% starch and 20% carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-52D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 5-Jul-2018

Weight of Sample*:	0.0171 g	**Filter Size:**	25 mm
Percent of Original Sample*:	66%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	50	1.5	33.3	Anthophyllite
2	25	1.5	16.6	Anthophyllite
3	10	0.5	20	Anthophyllite
4	19	1.0	19	Anthophyllite
5	11	1.0	11	Anthophyllite
6	9	1.0	9	Anthophyllite
7	30	0.8	37.5	Anthophyllite
8	8	0.25	32	Anthophyllite
9	3.5	0.25	14	Anthophyllite
AVERAGE	**18.4**	**0.87**	**21.2**	

Total Asbestos Structures:	9
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5
Asbestos Mass Fraction:	**0.0060%**
Asbestos Mass Fraction of Original Sample:	**0.0040%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-52D

Analyst: Lee Poye
Date: 5-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						
	A9		NSD						
	A10		NSD						
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		1	50 x 1.50	Anthophyllite	Yes	01	02	
	B5		2	25 x 1.50	Anthophyllite	Yes	03	04	
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
2	C1		3	10 x 0.50	Anthophyllite	Yes			
	C2		4	19 x 1.00	Anthophyllite	Yes	05	06	
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-52D

Analyst: Lee Poye
Date: 5-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
3	E1		NSD						
	E2		NSD						
	E3		NSD						
	E4		5	11 x 1.00	Anthophyllite	Yes			
	E5		NSD						
	E6		NSD						
	E7		NSD						
	E8		NSD						
	E9		NSD						
	E10		6	9 x 1.00	Anthophyllite	Yes			
	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		7	30 x 0.80	Anthophyllite	Yes	07	08	
	F9		8	8 x 0.25	Anthophyllite	Yes	09	10	
	F10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-52D

Analyst: Lee Poye
Date: 5-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						
	J1		9	3.5 x 0.25	Anthophyllite	Yes			
	J2		NSD						
	J3		NSD						
	J4		NSD						
	J5		NSD						
	J6		NSD						
	J7		NSD						
	J8		NSD						
	J9		NSD						
	J10		NSD						

Sample 20180061-52D
Structure 1 - Morphology

Sample 20180061-52D
Structure 1 – Diffraction Pattern

Sample 20180061-52D
Structure 2 - Morphology

StS-07 Full Quant_003
Anthophyllite
GO-B5
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 4000 x
J3 Resources, Inc.

Sample 20180061-52D
Structure 2 – Diffraction Pattern and EDS



Sample 20180061-52D
Structure 4 - Morphology



StS-07 Full Quant_005
Anthophyllite
GO-C2
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 4000 x
J3 Resources, Inc.

Sample 20180061-52D
Structure 4 – Diffraction Pattern and EDS

Sample 20180061-52D
Structure 7 - Morphology

StS-07 Full Quant_007
Anthophyllite
GO-F8
Microscopist: LWP

4 µm
HV=100kV
Direct Mag: 3000 x
J3 Resources, Inc.

Sample 20180061-52D
Structure 7 – Diffraction Pattern and EDS



STS-07 Full Quant_008
Anthophyllite - SAED
GO-FB
Microscopist: LWP

0.2 (1/A)
HV=100kV
Cam Len: 0.8000 m
J3 Resources, Inc.



Sample 20180061-52D
Structure 8 - Morphology



StS-07 Full Quant_009
Anthophyllite
GO-F9
Microscopist: LWP

1 µm
HV=100kV
Direct Mag: 12000 x
J3 Resources, Inc.

Sample 20180061-52D
Structure 8 – Diffraction Pattern and EDS





Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-52D



No Amphibole Peak Present

Sample 20180061-63D

(J3 Lab ID: STS 1608A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-63D

The sample was a white powder containing 60% medium to large platy Talc particles (100µm to >200µm in size). The remaining 40% percent was composed of 20% starch and 20% carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-63D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 5-Jul-2018

Weight of Sample*:	0.0177 g	**Filter Size:**	25 mm
Percent of Original Sample*:	67%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	13	0.4	32.5	Anthophyllite
AVERAGE	13	0.4	32.5	

Total Asbestos Structures:	1
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5
Asbestos Mass Fraction:	**0.000053%**
Asbestos Mass Fraction of Original Sample:	**0.000035%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-63D

Analyst: Lee Poye
Date: 5-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		1	13 x 0.40	Anthophyllite	Yes			
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
2	E1		NSD						
	E2		NSD						
	E3		NSD						
	E4		NSD						
	E5		NSD						
	E6		NSD						
	E7		NSD						
	E8		NSD						
	E9		NSD						
	E10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-63D

Analyst: Lee Poye
Date: 5-Jul-2018

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						
3	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-63D

Analyst: Lee Poye
Date: 5-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						
	A9		NSD						
	A10		NSD						
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						

Sample 20180061-63D
Structure 1 – EDS



Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-63D



No Amphibole Peak Present

Sample 20180061-65D

(J3 Lab ID: STS 1609A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-65D

The sample was a white powder containing 60% medium to large platy Talc particles (100µm to >200µm in size). The remaining 40% percent was composed of 20% starch and 20% carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-65D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 6-Jul-2018

Weight of Sample*:	0.0179 g	**Filter Size:**	25 mm
Percent of Original Sample*:	68%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure #	Length (um)	Width (um)	Aspect Ratio	Asbestos Type
1	17	1.5	11.3	Anthophyllite
2	13	1.5	8.7	Anthophyllite
3	20	1.3	15.3	Anthophyllite
4	10.5	0.5	21	Anthophyllite
5	5.8	0.5	11.6	Anthophyllite
6	12	0.5	24	Anthophyllite
7	18	1.4	12.9	Anthophyllite
8	15	0.2	75	Anthophyllite
9	16	2.5	6.4	Anthophyllite
10	9	1.2	7.5	Anthophyllite
11	10	0.5	20	Anthophyllite
12	8.5	0.25	34	Anthophyllite
13	23	3.5	6.6	Anthophyllite
AVERAGE	13.7	1.18	11.6	

Total Asbestos Structures:	13
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5
Asbestos Mass Fraction:	**0.014%**
Asbestos Mass Fraction of Original Sample:	**0.0092%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-65D

Analyst: Lee Poye
Date: 6-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	D1		1	17 x 1.50	Anthophyllite	Yes			
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		2	13 x 1.50	Anthophyllite	Yes	01	02	Zone Axis [1 2 1]
	D9		NSD						
	D10		NSD						
	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		3	20 x 1.30	Anthophyllite	Yes	03	04	Zone Axis [1 0 0]
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						
2	F1		4	10.5 x 0.50	Anthophyllite	Yes	05	06	
	F2		5	5.8 x 0.50	Anthophyllite	Yes	07	08	
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-65D

Analyst: Lee Poye
Date: 6-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10		NSD						
3	C1		6	12 x 0.50	Anthophyllite	Yes			
	C2		7	18 x 1.40	Anthophyllite	Yes			
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		8	15 x 0.20	Anthophyllite	Yes			
	C10		NSD						
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		9	16 x 2.50	Anthophyllite	Yes			
			10	9 x 1.20	Anthophyllite	Yes			
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-65D

Analyst: Lee Poye
Date: 6-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	E1		NSD						
	E2		11	10 x 0.50	Anthophyllite	Yes			
	E3		12	8.5 x 0.25	Anthophyllite	Yes			
	E4		NSD						
	E5		NSD						
	E6		NSD						
	E7		NSD						
	E8		NSD						
	E9		NSD						
	E10		NSD						
	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		13	23 x 3.50	Anthophyllite	Yes			

Sample 20180061-65D
Structure 2 - Morphology

Sample 20180061-65D
Structure 2 – Diffraction Pattern and EDS



STS-09 Full Quant_002
Anthophyllite - SAED ZA [1 2 1]
GO-D8
Microscopist: LWP

0.2 (1/Å)
HV=100kV
Cam Len: 0.8000 m
J3 Resources, Inc.



Sample 20180061-65D
Structure 3 - Morphology

Sample 20180061-65D
Structure 3 – Diffraction Pattern and EDS



Sample 20180061-65D
Structure 4 - Morphology



Sample 20180061-65D
Structure 4 – Diffraction Pattern and EDS



Sample 20180061-65D
Structure 5 - Morphology



StS-09 Full Quant_007
Anthophyllite
GO-F2
Microscopist: LWP

1 µm
HV=100kV
Direct Mag: 15000 x
J3 Resources, Inc.

Sample 20180061-65D
Structure 5 – Diffraction Pattern

Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-65D



No Amphibole Peak Present

Sample 20180061-66D

(J3 Lab ID: STS 1610A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-66D

The sample was a white powder containing 85% medium to large platy Talc particles (100µm to >200µm in size) and Talc rods. The remaining 15% percent was composed of carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-66D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 7-Jul-2018

Weight of Sample*:	0.0177 g	**Filter Size:**	25 mm
Percent of Original Sample*:	79%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
N/D	N/A	N/A	N/A	None Detected
AVERAGE	N/A	N/A	N/A	

Total Asbestos Structures: 0

Asbestos Mass Fraction: < 0.000000032%

Asbestos Mass Fraction of Original Sample: < 0.000000025%

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-66D

Analyst: Lee Poye
Date: 7-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						
2	E1		NSD						
	E2		NSD						
	E3		NSD						
	E4		NSD						
	E5		NSD						
	E6		NSD						
	E7		NSD						
	E8		NSD						
	E9		NSD						
	E10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-66D

Analyst: Lee Poye
Date: 7-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						
3	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10		NSD						
	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-66D

Analyst: Lee Poye
Date: 7-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						
	J1		NSD						
	J2		NSD						
	J3		NSD						
	J4		NSD						
	J5		NSD						
	J6		NSD						
	J7		NSD						
	J8		NSD						
	J9		NSD						
	J10		NSD						

Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-66D



No Amphibole Peak Present

Sample 20180061-02D

(J3 Lab ID: STS 1611A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-02D

The sample was a white powder containing 85% medium to large platy Talc particles (100µm to >200µm in size) and Talc rods. The remaining 15% percent was composed of carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-02D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 7-Jul-2018

Weight of Sample*:	0.0179 g	**Filter Size:**	25 mm
Percent of Original Sample*:	80%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
N/D	N/A	N/A	N/A	None Detected
AVERAGE	N/A	N/A	N/A	

Total Asbestos Structures: 0

Asbestos Mass Fraction: < 0.000000031%

Asbestos Mass Fraction of Original Sample: < 0.000000025%

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-02D

Analyst: Lee Poye
Date: 7-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						
	A9		NSD						
	A10		NSD						
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
2	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5	✓	NA	21 x 1.30	Talc	Yes			Fiber
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-02D

Analyst: Lee Poye
Date: 7-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						
3	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						
	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-02D

Analyst: Lee Poye
Date: 7-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						
	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						

Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-02D



No Amphibole Peak Present

Sample 20180061-10D

(J3 Lab ID: STS 1612A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-10D

The sample was a white powder containing 60% medium to large platy Talc particles (100µm to >200µm in size). The remaining 40% percent was composed of 20% starch and 20% carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-10D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 9-Jul-2018

Weight of Sample*:	0.0172 g	**Filter Size:**	25 mm
Percent of Original Sample*:	69%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	9.2	0.4	23	Anthophyllite
AVERAGE	9.2	0.4	23	

Total Asbestos Structures:	1
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5
Asbestos Mass Fraction:	**0.000038%**
Asbestos Mass Fraction of Original Sample:	**0.000026%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-10D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						
	A9		NSD						
	A10		NSD						
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
2	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-10D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	J1		NSD						
	J2		NSD						
	J3		NSD						
	J4		NSD						
	J5		NSD						
	J6		NSD						
	J7		NSD						
	J8		NSD						
	J9		NSD						
	J10		NSD						
3	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-10D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
	E1		NSD						
	E2		NSD						
	E3		NSD						
	E4		NSD						
	E5		NSD						
	E6		NSD						
	E7		NSD						
	E8		NSD						
	E9		1	9.2 x 0.40	Anthophyllite	Yes	01	02	
	E10		NSD						

Sample 20180061-10D
Structure 1 - Morphology



StS-12 Full Quant_001
Anthophyllite
GO-E9
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 7500 x
J3 Resources, Inc.

Sample 20180061-10D
Structure 1 – Diffraction Pattern and EDS





Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-10D



No Amphibole Peak Present

Sample 20180061-15D

(J3 Lab ID: STS 1613A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-15D

The sample was a white powder containing 85% medium to large platy Talc particles (100µm to >200µm in size) and Talc rods. The remaining 15% percent was composed of carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images

100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-15D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 9-Jul-2018

Weight of Sample*:	0.0174 g	**Filter Size:**	25 mm
Percent of Original Sample*:	78%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	6	0.5	12	Anthophyllite
2	5	0.25	20	Anthophyllite
3	19	0.9	21.1	Anthophyllite
4	33	1.2	27.5	Anthophyllite
5	5	0.25	20	Anthophyllite
6	5.3	0.3	17.7	Anthophyllite
7	5.5	0.6	9.2	Anthophyllite
AVERAGE	11.3	0.57	9.7	

Total Asbestos Structures:	7
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5

Asbestos Mass Fraction:	**0.0017%**
Asbestos Mass Fraction of Original Sample:	**0.0013%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-15D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		1	6 x 0.50	Anthophyllite	Yes	01	02	
	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		2	5 x 0.25	Anthophyllite	Yes			
	D6		3	19 x 0.90	Anthophyllite	Yes	03	04	
	D7		4	33 x 1.20	Anthophyllite	Yes	05	06	
	D8		NSD						
	D9		NSD						
	D10		NSD						
2	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						
	A9		NSD						
	A10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-15D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						
3	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		5	5 x 0.25	Anthophyllite	Yes	07	08	
	F10		NSD						
	J1		NSD						
	J2		NSD						
	J3		NSD						
	J4		NSD						
	J5		NSD						
	J6		NSD						
	J7		NSD						
	J8		NSD						
	J9		NSD						
	J10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-15D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						
	J1		6	5.3 x 0.30	Anthophyllite	Yes			
	J2		NSD						
	J3		NSD						
	J4		NSD						
	J5		NSD						
	J6		NSD						
	J7		NSD						
	J8		7	5.5 x 0.60	Anthophyllite	Yes			
	J9		NSD						
	J10		NSD						

Sample 20180061-15D
Structure 1 - Morphology

SIS-13 Full Quant_001
Anthophyllite
GO-C10
Microscopist: LWP

1 µm
HV=100kV
Direct Mag: 12000 x
J3 Resources, Inc.

Sample 20180061-15D
Structure 1 – Diffraction Pattern

Sample 20180061-15D
Structure 3 - Morphology



Sample 20180061-15D
Structure 3 – Diffraction Pattern



Sample 20180061-15D
Structure 4 - Morphology

StS-13 Full Quant_005
Anthophyllite
GO-D7
Microscopist: LWP

6 µm
HV=100kV
Direct Mag: 2500 x
J3 Resources, Inc.

Sample 20180061-15D
Structure 4 – Diffraction Pattern and EDS





resources, inc.

Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-15D



No Amphibole Peak Present

Sample 20180061-21D

(J3 Lab ID: STS 1614A)



Sample as received by J3 Resources, Inc.

J3 resources, inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-21D

The sample was a white powder containing 60% medium to large platy Talc particles (100µm to >200µm in size). The remaining 40% percent was composed of 20% starch and 20% carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-21D

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 9-Jul-2018

Weight of Sample*:	0.0173 g	**Filter Size:**	25 mm
Percent of Original Sample*:	68%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
N/D	N/A	N/A	N/A	None Detected
AVERAGE	N/A	N/A	N/A	

Total Asbestos Structures: 0

Asbestos Mass Fraction: < 0.000000032%

Asbestos Mass Fraction of Original Sample: < 0.000000022%

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-21D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						
	A9		NSD						
	A10		NSD						
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
2	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-21D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	G1		NSD						
	G2		NSD						
	G3	✓	NA	21.5 x 1.50	Talc	Yes	01	02	Fiber
	G4		NSD						
	G5		NSD						
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10		NSD						
3	F1		NSD						
	F2		NSD						
	F3		NSD						
	F4		NSD						
	F5		NSD						
	F6		NSD						
	F7		NSD						
	F8		NSD						
	F9		NSD						
	F10		NSD						
	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-21D

Analyst: Lee Poye
Date: 9-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						
	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						

Sample 20180061-21D
Talc (GO G3) - Morphology

Sample 20180061-21D
Talc (GO G3) - Diffraction Pattern and EDS





Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-21D



No Amphibole Peak Present

Sample 20180061-31F

(J3 Lab ID: STS 1615A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-31F

The sample was a white powder containing 60% medium to large platy Talc particles (100µm to >200µm in size). The remaining 40% percent was composed of 20% starch and 20% carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-31F

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 10-Jul-2018

Weight of Sample*:	0.0179 g	**Filter Size:**	25 mm
Percent of Original Sample*:	67%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	43	2	21.5	Anthophyllite
2	4.5	0.25	18	Anthophyllite
3	7	0.5	14	Anthophyllite
AVERAGE	**18.2**	**0.92**	**19.8**	

Total Asbestos Structures:	3
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5
Asbestos Mass Fraction:	**0.0044%**
Asbestos Mass Fraction of Original Sample:	**0.0029%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-31F

Analyst: Lee Poye
Date: 10-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		NSD						
	A7		NSD						
	A8		NSD						
	A9		NSD						
	A10		NSD						
	B1		NSD						
	B2		1	43 x 2.00	Anthophyllite	Yes	01	02	Zone Axis [1 0 1]
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
2	C1		2	4.5 x 0.25	Anthophyllite	Yes			
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-31F

Analyst: Lee Poye
Date: 10-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (μm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		3	7 x 0.50	Anthophyllite	Yes			
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
3	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		NSD						
	D8		NSD						
	D9		NSD						
	D10		NSD						
	I1		NSD						
	I2		NSD						
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-31F

Analyst: Lee Poye
Date: 10-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5	✓	NA	10 x 1.00	Talc	Yes			Fiber
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
	C1		NSD						
	C2		NSD						
	C3		NSD						
	C4		NSD						
	C5		NSD						
	C6		NSD						
	C7		NSD						
	C8		NSD						
	C9		NSD						
	C10		NSD						

Sample 20180061-31F
Structure 1 - Morphology



StS-15 Full Quant_001
Anthophyllite
GO-B2
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 4000 x
J3 Resources, Inc.

Sample 20180061-31F
Structure 1 – Diffraction Pattern and EDS





Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-31F



No Amphibole Peak Present

Sample 20180061-31G

(J3 Lab ID: STS 1616A)



Sample as received by J3 Resources, Inc.

Determination of Asbestos in Talc by PLM

ISO 22262-1:2014

Sample 20180061-31G

The sample was a white powder containing 60% medium to large platy Talc particles (100µm to >200µm in size). The remaining 40% percent was composed of 20% starch and 20% carbonate material.

No asbestos was detected by PLM.

Polarized Light Microscope Images



100X Magnification of Talc Particles Crossed polars and 530nm gypsum compensator plate



100X Magnification dispersion staining of Talc Particles 1.550 refractive index oil

Determination of Asbestos in Talc by ATEM

ISO 22262-2:2014

Sample 20180061-31G

J3 Order #: JH1898969 **Analyst:** Lee Poye

Customer: Joseph Satterley, Esq. **Date:** 10-Jul-2018

Weight of Sample*:	0.0174 g	**Filter Size:**	25 mm
Percent of Original Sample*:	65%	**Filter Pore Size:**	0.2 µm
Suspension Volume:	1.5 mL	**Area of Analytical Filter:**	210 mm^2
Filtered Suspension Volume:	0.1 mL	**GO Size:**	0.0132 mm^2
		GO Area Analyzed:	1.056 mm^2

Results Summary

Asbestos Structure Number	Length (µm)	Width (µm)	Aspect Ratio	Asbestos Type
1	26	0.5	52	Anthophyllite
2	18	0.5	36	Anthophyllite
3	5	0.5	10	Anthophyllite
4	19	1	19	Anthophyllite
AVERAGE	**17**	**0.63**	**27.2**	

Total Asbestos Structures:	4
Anthophyllite Density:	3000 kg/m^3
Cross-section Shape Factor (Amphibole):	0.5
Asbestos Mass Fraction:	**0.00080%**
Asbestos Mass Fraction of Original Sample:	**0.00052%**

* Sample was previously gravimetrically reduced.

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-31G

Analyst: Lee Poye
Date: 10-Jul-2018
Page: 1 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
1	A1		NSD						
	A2		NSD						
	A3		NSD						
	A4		NSD						
	A5		NSD						
	A6		1	26 x 0.50	Anthophyllite	Yes	02	01	
	A7		NSD						
	A8		NSD						
	A9		NSD						
	A10		NSD						
	B1		NSD						
	B2		NSD						
	B3		NSD						
	B4		NSD						
	B5		NSD						
	B6		NSD						
	B7		NSD						
	B8		NSD						
	B9		NSD						
	B10		NSD						
2	D1		NSD						
	D2		NSD						
	D3		NSD						
	D4		NSD						
	D5		NSD						
	D6		NSD						
	D7		2	18 x 0.50	Anthophyllite	Yes			
	D8		NSD						
	D9		NSD						
	D10		3	5 x 0.50	Anthophyllite	Yes	03	04	Zone Axis [3 0 1]

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-31G

Analyst: Lee Poye
Date: 10-Jul-2018
Page: 2 of 3

Magnification Scan at 3,000X									
Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
2	E1		NSD						
	E2		NSD						
	E3		NSD						
	E4		NSD						
	E5		NSD						
	E6		NSD						
	E7		NSD						
	E8		NSD						
	E9	✓	NA	7.2 x 0.40	Talc	Yes			Fiber
	E10		NSD						
3	G1		NSD						
	G2		NSD						
	G3		NSD						
	G4		NSD						
	G5		NSD						
	G6		NSD						
	G7		NSD						
	G8		NSD						
	G9		NSD						
	G10		NSD						
	H1		NSD						
	H2		NSD						
	H3		NSD						
	H4		NSD						
	H5		NSD						
	H6		NSD						
	H7		NSD						
	H8		NSD						
	H9		NSD						
	H10		NSD						

Determination of Asbestos in Talc by ATEM

LAB WORKSHEET

Customer: Joseph Satterley, Esq.
J3 Order #: JH1898969
Sample #: 20180061-31G

Analyst: Lee Poye
Date: 10-Jul-2018
Page: 3 of 3

Magnification Scan at 3,000X

Grid	G.O. #	Non-Asbestos	Asbestos Tally	L x W (µm)	TYPE	Images			Comments
						EDS	Morphology	SAED	
4	I1		NSD						
	I2		4	19 x 1.00	Anthophyllite	Yes			
	I3		NSD						
	I4		NSD						
	I5		NSD						
	I6		NSD						
	I7		NSD						
	I8		NSD						
	I9		NSD						
	I10		NSD						
	J1		NSD						
	J2	✓	NA	14 x 1.70	Talc	Yes			Fiber
	J3		NSD						
	J4		NSD						
	J5		NSD						
	J6		NSD						
	J7		NSD						
	J8		NSD						
	J9		NSD						
	J10		NSD						

Sample 20180061-31G
Structure 1 - Morphology



StS-16 Full Quant_002
Anthophyllite
GD - A6
Microscopist: LWP

2 µm
HV=100kV
Direct Mag: 4000 x
J3 Resources, Inc.

Sample 20180061-31G
Structure 1 – Diffraction Pattern and EDS



Sample 20180061-31G
Structure 3 - Morphology



StS-16 Full Quant_003
Anthophyllite
GO - D10
Microscopist: LWP

1 µm
HV=100kV
Direct Mag: 12000 x
J3 Resources, Inc.

Sample 20180061-31G
Structure 3 – Diffraction Pattern and EDS



Determination of Asbestos in Talc by XRD

ISO 22262-3:2016

Sample 20180061-31G



No Amphibole Peak Present

APPENDIX C

CHAIN OF CUSTODY

98969

Joseph D. Satterley*
Paul J. Kelley
Paul J. Ivie
J. Eric Kiser

SATTERLEY & KELLEY PLLC

Of Counsel:
Robert L. Catlett, Jr.

Paralegals:
Tammy Owens Walker
Amanda Sanders
Courtney Lincks

May 22, 2018

Via Federal Express

Lee W. Poye, Vice President
J3 Resources, Inc.
6110 W. 34th St.
Houston, TX 77092

Re: ***Hayes v. Colgate, et al.***
Shower to Shower Samples

Dear Mr. Poye:

Enclosed, please find the following sixteen (16) containers of Shower to Shower samples obtained at Alliance Technologies on May 17, 2018.

Sample 20180070-07D (J&J Box 1- 2014.1.397D)
Sample 20180061-37D (STS Sample 02 Done- STS 001 D)
Sample 20180061-38D (STS Sample 02 Done- STS 002 D)
Sample 20180061-45D (STS Sample 02 Done- STS 009 D)
Sample 20180061-50D (STS Sample 02 Done- STS 014 D)
Sample 20180061-51D (STS Sample 02 Done- STS 015 D)
Sample 20180061-52D (STS Sample 02 Done- STS 016 D)
Sample 20180061-63D (STS Sample 02 Done- STS 027 D)
Sample 20180061-65D (STS Sample 02 Done- STS 029 D)
Sample 20180061-66D (STS Sample 02 Done- STS 030 D)
Sample 20180061-02D (STS Sample 01 Done- STS 036 D)
Sample 20180061-10D (STS Sample 01 Done- STS 044 D)
Sample 20180061-15D (STS Sample 01 Done- STS 049 D)
Sample 20180061-21D (STS Sample 01 Done- STS 055 D)
Sample 20180061-31F (STS Sample 01 Done- STS 065 F-Regular)
Sample 20180061-31G (STS Sample 01 Done- STS 065G-Spice)

I am also enclosing the Joint Catalogue for each sample identified above. Please note on the Joint Catalogues, the samples given to the Estate of Donna Hayes are referenced as Sample D, except for the two samples of 31 which are labeled F and G. Please give me a call upon receipt.

Rec'd 23-May-2018
Lee Poye V.P.
J3 Resources, Inc

Sincerely,

Joseph D. Satterley

JDS/tow
Enclosures

EXHIBIT E

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
20180070-07	2014.001.0397	Shower to Shower Deodorant Body Powder	1978	8 oz.	~7.3oz.	~3.66 oz.
20180070-07A						~1.32 oz.
20180070-07B						~1.84 oz.
20180070-07C						NOT USED
20180070-07D						~0.48 oz.

Observer for plaintiffs hereby acknowledges receipt of 20180070-07A, ~1.32oz. (weight) of original Sample 20180070-07.

Observer for Plaintiffs — Date: 5/17/18

* 20180070-07A will be held at the Laboratory and shipped to the MDL PEC separately. AMK

Observer for plaintiffs hereby acknowledges receipt of 20180070-07D, 0.48oz. AMK (weight) of original Sample 20180070-07.

Observer for Plaintiffs — Date: 5/17/18

Observer for defendants hereby acknowledges receipt of 20180070-07B, ~1.84oz. (weight) of original Sample 20180070-07.

Observer for Defendants — Date: 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 20180070-07 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (20180070-07C).

Laboratory Technician — Date: 5/17/18

This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180070-07D
J & J Box 1 - 2014.1.397 D
Jack N. Frost, Jr.





EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR RECEPTACLE BEFORE DIVISION	QUANTITY IN ORIGINAL CONTAINER/RECEPTACLE OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 37	STS001	Morning Fresh Scent Shower to Shower Deodorant Body Powder with Baking Soda	1982	8 oz.		
2018 0061 - 37 C					~4.49 oz.	~4.03 oz.
2018 0061 - 37 D						~0.46 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 37 D, ~0.46 oz. (weight) of 2018 0061 - 37C

Observer for Plaintiffs — Date: 5/17/18

Observer for defendants hereby acknowledges witnessing the same.

Observer for Defendants — Date: 5/17/18

Laboratory technician hereby acknowledges that all remaining material from 2018 0061 - 37C was returned to its original container or receptacle.

Laboratory Technician — Date: 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-37D
Drinker
STS SAMPLE 02 DONE - STS 001 D
Jack N. Frost, Jr.


20180061-370
STS SAMPLE 02 DOME
Jack N. Frost, Jr.

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR RECEPTACLE BEFORE DIVISION	QUANTITY IN ORIGINAL CONTAINER/RECEPTACLE OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 38	STS002	IMPROVED! Shower to Shower DEODORANT BODY POWDER with Baking Soda	1980	8 oz.		
2018 0061 - 38 C					~4.15 oz.	~3.67 oz.
2018 0061 - 38 D						~0.48 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 38 D, ~0.48 oz. (weight) of 2018 0061 - 38C.

Observer for Plaintiffs — Date: 5/17/18

Observer for defendants hereby acknowledges witnessing the same.

Observer for Defendants — Date: 5/17/18

Laboratory technician hereby acknowledges that all remaining material from 2018 0061 - 38C was returned to its original container or receptacle.

Laboratory Technician — Date: 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-38D
Drinker
STS SAMPLE 02 DONE - STS 002 D
Jack N. Frost, Jr.



EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 45	STS009	MORNING FRESH SCENT Shower to Shower DEODORANT BODY POWDER with Baking Soda	1982	13 oz.	~14.03oz	~ 7.03 oz.
2018 0061 - 45 A						~ 2.96 oz.
2018 0061 - 45 B						~ 3.54 oz.
2018 0061 - 45 C						NOT USED
2018 0061 - 45 D						~ 0.50 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 45 A, ~2.96oz (weight) of original Sample 2018 0061 - 45

Observer for Plaintiffs — Date 5/17/18

* 20180061-45A will be held at the Laboratory and shipped to the MDL PEC separately. AMK

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 45 D, ~0.50oz (weight) of original Sample 2018 0061 - 45.

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges receipt of 2018 0061 - 45 B, ~3.54oz (weight) of original Sample 2018 0061 - 45.

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 2018 0061 - 45 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (2018 ____ - ____ C).

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-45D
Drinker
STS SAMPLE 02 DONE - STS 009 D
Jack N. Frost, Jr.




1.26

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 50	STS014	Shower to Shower DEODORANT BODY POWDER with Baking Soda	1978	4 oz.	~3.92 oz.	~1.97 oz.
2018 0061 - 50 A						~0.57 oz.
2018 0061 - 50 B						~0.87 oz.
2018 0061 - 50 C						NOT USED
2018 0061 - 50 D						~0.51 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 50 A, ~0.57 oz (weight) of original Sample 2018 0061 - 50.

Observer for Plaintiffs — Date 5/17/18

* 20180061-50A will be held at the laboratory and shipped to the MDL PEC separately. AML

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 50 D, ~0.51 oz (weight) of original Sample 2018 0061 - 50.

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges receipt of 2018 0061 - 50 B, ~0.87 oz (weight) of original Sample 2018 0061 - 50.

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 2018 0061 - 50 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (2018 ____ - ____ C).

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-50D
Drinker
STS SAMPLE 02 DONE - STS 014 D
Jack N. Frost, Jr.



EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 51	STS015	MORNING FRESH SCENT Shower to Shower DEODORANT BODY POWDER with Baking Soda	1982	8 oz.	~8.03oz.	~4.03oz.
2018 0061 - 51 A						~1.73oz.
2018 0061 - 51 B						~1.78 oz.
2018 0061 - 51 C						NOT USED
2018 0061 - 51 D						~0.49oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 51 A, ~1.73oz. (weight) of original Sample 2018 0061 - 51

Observer for Plaintiffs — Date 5/17/18

† 20180061-51A will be held at the Laboratory and shipped to the MDL PSC Separately. AMW

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 51 D, ~0.49oz. (weight) of original Sample 2018 0061 - 51

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges receipt of 2018 0061 - 51 B, ~1.78oz. (weight) of original Sample 2018 0061 - 51

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 2018 0061 - 51 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (2018 ____ - ____ C).

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-51D
Drinker
STS SAMPLE 02 DONE - STS 015 D
Jack N. Frost, Jr.


1.75

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR RECEPTACLE BEFORE DIVISION	QUANTITY IN ORIGINAL CONTAINER/RECEPTACLE OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 52	STS016	IMPROVED! Shower to Shower DEODORANT BODY POWDER with Baking Soda	1980-1981	13oz.	~6.30 oz.	~ 5.80 oz.
2018 0061 - 52 C					NOT USED	NOT USED
2018 0061 - 52 D						~ 0.5 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 52 D, ~0.5 oz. (weight) of 2018 0061 - 52.

Observer for Plaintiffs — 5/17/18 Date

Observer for defendants hereby acknowledges witnessing the same.

Observer for Defendants — 5/17/18 Date

Laboratory technician hereby acknowledges that all remaining material from 2018 0061 - 52 was returned to its original container or receptacle.

Laboratory Technician — 5/17/18 Date

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-52D
Drinker
STS SAMPLE 02 DONE · STS 016 D
Jack N. Frost, Jr.


20180061-S2
STS SAMPLE
Jack N. Fra
1.74



EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 63	STS027	IMPROVED! Shower to Shower DEODORANT BODY POWDER with Baking Soda	1980	13 oz.	~13.17 oz.	~ 6.60 oz.
2018 0061 - 63 A						~ 2.67 oz.
2018 0061 - 63 B						~ 3.39 oz.
2018 ~~0061 - 63~~ C						NOT USED
2018 0061 - 63 D						~ 0.51 oz

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 63 A. ~2.67 oz (weight) of original Sample 2018 0061 - 63

Observer for Plaintiffs — Date 5/17/18

* 20180061-63A will be held at the Laboratory and shipped to the MDL PEC separately. (AMK)

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 63 D. ~0.51 oz (weight) of original Sample 2018 0061 - 63

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges receipt of 2018 0061 - 63 B. ~3.39 oz (weight) of original Sample 2018 0061 - 63

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 2018 0061 - 63 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (2018 _____ - _____ C).

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-63D
Drinker
STS SAMPLE 02 DONE - STS 027 D
Jack N. Frost, Jr.

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 65	STS029	Shower to Shower DEODORANT BODY POWDER with Baking Soda	1980-1981	8 oz.	~ 8.50 oz.	~4.26 oz.
2018 0061 - 65 A						~ 1.83 oz.
2018 0061 - 65 B						~ 1.93 oz.
2018 0061 - 65 C						NOT USED
2018 0061 - 65 D						~ 0.48 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 65 A, ~1.83 oz. (weight) of original Sample 2018 0061 - 65

Observer for Plaintiffs — Date 5/17/18

* 20180061-65A will be held at the Laboratory and shipped to the MDL PEC separately. AM

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 65 D, ~0.48 oz. (weight) of original Sample 2018 0061 - 65.

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges receipt of 2018 0061 - 65 B, ~1.93 oz. (weight) of original Sample 2018 0061 - 65

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 2018 0061 - 65 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (2018 _____ - _____ C)

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-65D
Drinker
STS SAMPLE 02 DONE - STS 029 D
Jack N. Frost, Jr.


1.74



EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 66	STS030	MORNING FRESH SCENT Shower to Shower DEODORANT BODY POWDER with Baking Soda	1982	13 oz.	~14.52 oz.	~7.27 oz.
2018 0061 - 66A						~3.17 oz.
2018 0061 - 66B						~3.49 oz.
2018 0061 - 66C						NOT USED
2018 0061 - 66D						~0.59 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 66 A, ~3.17 oz. (weight) of original Sample 2018 0061 - 66.

Observer for Plaintiffs — Date 5/17/18

* 20180061-66A will be held at the Laboratory and shipped to the MDL PEC separately 100557 (AMK)

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 66 D, ~0.59 oz. (weight) of original Sample 2018 0061 - 66.

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges receipt of 2018 0061 - 66 B, ~3.49 oz. (weight) of original Sample 2018 0061 - 66.

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 2018 0061 - 66 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (2018 ____ - ____ C).

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


Drinker
20180061-66D
STS SAMPLE 02 DONE - STS 030 D
Jack N. Frost, Jr.


Drinker

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR RECEPTACLE BEFORE DIVISION	QUANTITY IN ORIGINAL CONTAINER/RECEPTACLE OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 02	STS036	Shower to Shower DEODORANT BODY POWDER with Baking Soda	1975	13 oz.	~ 6.31 oz.	~ 5.79 oz.
2018 0061 - 02 C					NOT USED	NOT USED
2018 0061 - 02 D						~ 0.51 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 02 D. ~0.51 oz. (weight) of 2018 0061 - 02.

Observer for Plaintiffs — 5/17/18 Date

Observer for defendants hereby acknowledges witnessing the same.

Observer for Defendants — 5/17/18 Date

Laboratory technician hereby acknowledges that all remaining material from 2018 0061 - 02 was returned to its original container or receptacle.

Laboratory Technician — 5/17/18 Date

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-02D
Drinker
STS SAMPLE 01 DONE - STS 036 D
Jack N. Frost, Jr.


20180061-02D
STS SAMPLE 01 DONE -STS
Jack N. Frost, Jr.



EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 10	STS044	IMPROVED! Shower to Shower DEODORANT BODY POWDER with Baking Soda	1980-1981	4 oz.	~3.67oz.	~1.84oz.
2018 0061 - 10 A						~0.40oz.
2018 0061 - 10 B						~0.98oz.
2018 0061 - 10 C						NOT USED
2018 0061 - 10 D						~0.45oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 10 A, ~0.40oz (weight) of original Sample 2018 0061 - 10

Observer for Plaintiffs — Date 5/17/18

* 2018 0061-10A will be held at the Laboratory and shipped to the MDL PEC separately. (Ann)

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 10 D, ~0.45oz (weight) of original Sample 2018 0061 - 10.

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges receipt of 2018 0061 - 10 B, ~0.98oz (weight) of original Sample 2018 0061 - 10.

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 2018 0061 - 10 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (2018 _____ - _____ C).

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-10D
Drinker
STS SAMPLE 01 DONE - STS 044 D
Jack N. Frost, Jr.


1.74

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	ACTUAL QUANTITY IN ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 15	STS049	Shower to Shower DEODORANT BODY POWDER with Baking Soda	1978	8 oz.	~7.59	~3.81 oz.
2018 0061 - 15 A						~1.19 oz.
2018 0061 - 15 B						~2.05 oz.
2018 0061 - 15 C						NOT USED
2018 0061 - 15 D						~0.54 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 15 A, ~1.19 oz. (weight) of original Sample 2018 0061 - 15.

Observer for Plaintiffs — Date 5/17/18

20180061-15A will be held at the Laboratory and shipped to the MDL PEC separately. (AMK)

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 15 D, ~0.54 oz. (weight) of original Sample 2018 0061 - 15.

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges receipt of 2018 0061 - 15 B, ~2.05 oz. (weight) of original Sample 2018 0061 - 15.

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from Sample 2018 0061 - 15 was

(check one): ☑ replaced in its original container ☐ transferred to a new receptacle (2018 _____ - _____ C).

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


Drinker
20180061-15D
STS SAMPLE 01 DONE - STS 049 D
Jack N. Frost, Jr.

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR RECEPTACLE BEFORE DIVISION	QUANTITY IN ORIGINAL CONTAINER/RECEPTACLE OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 21	STS055	REGULAR SCENT Shower to Shower DEODORANT BODY POWDER with Baking Soda and Corn Starch	1983	8 oz.	AMK ~~~4.3 oz.~~	
2018 0061 - 21 C					~ 4.3 oz.	~ 3.80 oz.
2018 0061 - 21 D						~ 0.5 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 21 D, ~0.5 oz. (weight) of 2018 0061 - 21C.

Observer for Plaintiffs — 5/17/18 Date

Observer for defendants hereby acknowledges witnessing the same.

Observer for Defendants — 5/17/18 Date

Laboratory technician hereby acknowledges that all remaining material from 2018 0061 - 21C was returned to its original container or receptacle.

Laboratory Technician — 5/17/18 Date

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-21D
Drinker
STS SAMPLE 01 DONE - STS 055 D
Jack N. Frost, Jr.


1.73

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR RECEPTACLE BEFORE DIVISION	QUANTITY IN ORIGINAL CONTAINER/RECEPTACLE OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 31	STS065	REGULAR SCENT Shower to Shower DEODORANT BODY POWDER With Baking Soda and Cornstarch	1986	8 oz.	~3.88oz.	~3.42 oz.
~~2018 0061 - 31 C~~					NOT USED	NOT USED
2018 0061 - 31 ■F AMK						~0.46 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 31 F ■ ~0.46oz. of 2018 0061 - 31.
AMK (weight)

Observer for Plaintiffs — Date 5/17/18

Observer for defendants hereby acknowledges witnessing the same.

Observer for Defendants — Date 5/17/18

Laboratory technician hereby acknowledges that all remaining material from 2018 0061 - 31 was returned to its original container or receptacle.

Laboratory Technician — Date 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-31F Regular Drinker
STS SAMPLE 01 DONE - STS 065F
Jack N. Frost, Jr.


20180061-31F
STS SAMPLE 01 DONE
Jack N. Frost, Jr.

EXHIBIT E[1]

IN RE JOHNSON & JOHNSON TALCUM POWDER PRODUCTS
MARKETING, SALES PRACTICES, AND PRODUCTS LIABILITY LITIGATION
MDL NO. 16-2738 (FLW) (LHG)

JOINT CATALOGUE

LABORATORY CONTROL NO.	SAMPLE IDENTIFICATION NO.	LABEL ON ORIGINAL CONTAINER	DATE ON ORIGINAL CONTAINER	QUANTITY ON LABEL OF ORIGINAL CONTAINER	QUANTITY IN ORIGINAL CONTAINER OR RECEPTACLE BEFORE DIVISION	QUANTITY IN ORIGINAL CONTAINER/RECEPTACLE OR NEW RECEPTACLE AFTER DIVISION
2018 0061 - 31	STS 065	SPICE SCENT Shower to Shower DEODORANT BODY POWDER with Baking Soda and Corn Starch	1986	8 oz.	~3.94 oz.	~3.43 oz.
2018 0061 - 31 C					NOT USED	NOT USED
2018 0061 - 31 G AMK						~0.51 oz.

Observer for plaintiffs hereby acknowledges receipt of 2018 0061 - 31 G AMK ~0.51 oz. (weight) of 2018 0061 - 31.

Observer for Plaintiffs — Date: 5/17/18

Observer for defendants hereby acknowledges witnessing the same.

Observer for Defendants — Date: 5/17/18

Laboratory technician hereby acknowledges that all remaining material from 2018 0061 - 31 was returned to its original container or receptacle.

Laboratory Technician — Date: 5/17/18

[1] This form is an Exhibit to the Agreed Order and Stipulation Regarding the Johnson & Johnson Defendants' Production of Talcum Powder Products and Talc Samples ("Agreed Order"). Terms used herein have the same meaning as defined in the Agreed Order. The instant form has been adapted for use in connection with the initial division of Samples STS009, STS014, STS015, STS027, STS029, STS030, STS044, STS049 and 2014.001.0397, and further division of Samples STS001, STS002, STS016, STS036, STS055 and STS065.


20180061-31G Spice Drinker
STS SAMPLE 01 DONE - STS 065G
Jack N. Frost, Jr.


20180061-31G
STS SAMPLE 01 DONE
Jack N. Frost, Jr.
[redacted]
1.76
5